

ISSN 2310-6697

toiser—open transactions on independent scientific-engineering research

FUNKTECHNIKPLUS # JOURNAL

Théorie—Expérimentation—Métrologie—Logiciel—Applications

ISSUE 4 – SATURDAY 31 MAY 2014 – YEAR 1

REPRINT

Parameters Affecting the Lifetime of Transformer Oil in Distribution Transformers: Parameter Monitoring of 50 Transformers from the Athens Area

M.G. Danikas, E. Rapti, I. Liapis, A.B.B.Abd. Ghani



*This small European Journal is
In the Defense of Honesty in Science and Ethics in Engineering*

Publisher – otoiser—open transactions on independent scientific engineering research, www.otoiser.org—info@otoiser.org, Hauptstraße 52, 2831 Scheiblingkirchen, Austria

Language – We declare the origins of the Journal by using in the cover page English, German and French, as well as, a Hellenic vignette. However, since we recognize the dominance of US English in the technical literature, we adopted it as the Journal's language, although it is not our native language.

Focus – We consider Radio–FUNK, which still creates a vivid impression of the untouchable, and its Technology–TECHNIK, from an Advanced–PLUS point of view, Plus–PLUS Telecommunications Engineering, Electrical Engineering and Computer Science, that is, we dynamically focus at any related scientific-engineering research regarding Théorie, Expérimentation, Métrologie, Logiciel, ou Applications.

Scope – We emphasize this scope broadness by extending the title of the Journal with a Doppelkreuz-Zeichen # which we use as a placeholder for substitution of our Editorial Team disciplines: # Telecommunications etc. as above, or # High Voltage, # Software Engineering, # Simulation etc. as below.

Frequency – We publish 3 issues per year: on 31st of January, on 31st of May, and on 30th of September, as well as, an extra issue every 3 papers and a volume every 2 years.

Editions – We increase the edition number of an issue only when is needed to reform one or more of its papers—thus to increase their version numbers—but we keep unchanged its 1st edition date shown on its front page and we number its pages sequentially from 1. We count the editions of *About* separately.

Format – We use a fixed-space font, hyphenation, justification, unfixed word spacing, and the uncommon for Journals A5 (half A4) page size to achieve WYSIWYG printing and clear reading of 2 to 4 side-by-side pages on wide-screen displays

Printing-on-Demand – We can email gratis PDFs at 300-4000 dpi in booklet page scaling of either brochure or book type.

Copyright – We publish under a Creative Commons Attribution, CC-BY 3.0 Unported or CC-BY 4.0 International, License only.

Please download the latest *About* edition from
about.ftpj.otoiser.org

Editorial Team

Electrical Engineering

High Voltage Engineering # Insulating Materials
Professor Michael Danikas, mdanikas@ee.duth.gr
EECE, Democritus University of Thrace, Greece

Electrical Machines # Renewable Energies # Electric Vehicles
Assistant Professor Athanasios Karlis, akarlis@ee.duth.gr
EECE, Democritus University of Thrace, Greece

Computer Science

Computer Engineering # Software Engineering # Cyber Security
Professor Vasilis Katos, vkatos@bournemouth.ac.uk
Head of Computer and Informatics Dept, Bournemouth Univ, UK

Internet Engineering # Learning Management Systems
Lecturer Sotirios Kontogiannis, skontog@gmail.com
Business Administration Dept, TEI, Western Macedonia, Greece

Hypercomputation # Fuzzy Computation # Digital Typography
Dr. Apostolos Syropoulos, asyropoulos@yahoo.com
BSc-Physics, MSc-Computer Science, PhD-Computer Science
Independent Researcher, Xanthi, Greece

Telecommunications Engineering

Applied EM Electromagnetics # Applied Mathematics
Dr. Nikolaos Berketis, nberketis@gmail.com
BSc-Mathematics, MSc-Applied Maths, PhD-Applied Mathematics
Independent Researcher, Athens, Greece

Antennas # Metrology # EM Software # Simulation # Virtual Labs

Applied EM # Education # FLOSS # Amateur Radio # Electronics
Dr. Nikolitsa Yannopoulou, yin@arg.op4.eu *
Diploma Eng-EE, MEng-Telecom-EECE, PhD-Eng-Antennas-EECE
Independent Researcher, Scheiblingkirchen, Austria

Dr. Petros Zimourtopoulos, pez@arg.op4.eu *
BSc-Physics, MSc-Radio-Electronics, PhD-Antennas-EE
Independent Researcher, Scheiblingkirchen, Austria

* Copy & Layout Editing – Proof Reading – Issue & Web Management

Technical Support

Konstantinos Kondylis, kkondylis@gmail.com
Diploma Eng-EECE, MEng-EECE, Doha, Qatar

Christos Koutsos, ckoutsos@gmail.com
Diploma Eng-EECE, MEng-EECE, Bratislava, Slovakia

Information for Authors

This is a small, but independent, low profile Journal, in which we are all—Authors, Reviewers, Readers, and Editors—free at last to be Peers in Knowledge, without suffering from Journal roles or positions, Professional—Amateur—Academic statuses, or established "impact factorizations", under the following guiding principles:

Authors – We know what Work means, we respect the Work of the Independent Researcher in Science and Engineering and we want to exhibit his Work. Thus, we decided to found this Free and Open Access Journal in which to publish this Work. Furthermore, as we care indeed for the Work of the technical author—especially a young or a beginner one—we strongly support the publication of his Work, as follows:

- 0 We do not demand from the author to transfer his own copyright to us. Instead, we only consider papers resulting from original research work only, and only if the author can assure us that he owns the copyright of his own paper as well as that he submits to the Journal either an original copy or a revised version of his own paper, for possible publication after review—or even for immediate republication, if this paper has already been published after review—but, in any case under a Creative Commons Attribution, CC-BY 3 Unported or CC-BY 4 International, License, only.
- 1 We encourage the author to submit his own paper written just in Basic English plus Technical Terminology.
- 2 We encourage the author even to select a pen name, which may drop it at any time to reveal his identity.
- 3 We encourage the author to submit an accepted for publication paper, which he was forced to decline that publication because it would be based on a review with unacceptable evaluation or derogatory comments.
- 4 We encourage the author to submit any paper that was rejected after a poor, impotent, inadequate, unreasonable, irresponsible, incompetent, or "just ticking" review.
- 5 We encourage the author to submit an unreviewed paper of his own that he uploaded on some Open Access repository.
- 6 We encourage the author to upload his published papers in our Journal to a truly Free Open repository like viXra.org.
- 7 We provide the author with a decent, express, peer review process, of up to just 4 weeks, by at least 2, either anonymous or onymous, reviewers.

- 8 We provide the author with the option to choose from 2 review processes: the traditional, anonymous, close one, as well as, a contemporary, onymous, open review in our private mailing list for Peer Discussion.
- 9 Under the Clause 0 : We immediately accept for publication a research paper directly resulting from a Project Report, or a Diploma-, Master-, or PhD-thesis, which already the author has successfully defended before a committee of experts, as long as he can mention 2 members of this committee who approved his Work.
- 10 Under the Clause 0 : We immediately accept for publication any paper which is not Openly Accessible on the Internet.
- 11 We immediately publish online a paper, as soon as it is accepted for publication in the Journal.
- 12 We quickly publish an extra issue—that is in excess of the 3 issues we publish a year—as soon as the review process of 3 papers is completed.

Reviewers – Every peer may voluntarily become a reviewer of the Journal in his skillfulness for as long as he wishes. In addition, each author of the Journal must review one paper in his expertness for each one of his published papers.

Readers – Every reader is a potential post-reviewer: we welcome comments and post-reviews in our private mailing list for Peer Discussion.

Editors – Every editor owns a PhD degree—to objectively prove that he really has the working experience of passing through the dominant publishing system. An editor pre-reviews a paper in order to check its compliance to our guiding principles and to select the appropriate reviewers of it. We can accept for consideration papers only in the expertise areas currently shown in the Editorial Team page, above. However, since we are very willing to amplify and extend the Scope of the Journal, we welcome the volunteer expert, in any related subject, who wants to join the Editorial Team as long as he unreservedly accepts our guiding principles.

Electronic Publishing

We regularly use the Free Libre Open Source Software Libre Office with the Free Liberation Mono font and the Freewares PDFCreator and PDF-Xchange Viewer. We also use, with some basic html code of ours: the Free Open Source Software Open Journal System OJS by the Public Knowledge Project PKP installed in our website, and the Free Open Digital Library of

About

Internet Archive website, where we upload Issues, Paper reprints, *About* documents, and Volumes, in both portrait and landscape orientations, for exceptionally clear online reading with the Free Open Source BookReader.

Submissions

We can consider only papers submitted in a format which is fully compatible with LibreOffice—preferably in odt format.

Legal Notice – It is taken for granted that the submitter–correspondent author accepts, without any reservation, the totality of our publication conditions as they are analytically detailed here, in this *About*, as well as, that he also carries, in the case of a paper by multiple authors, the independent will of each one of his coauthors to unreservedly accept all the aforementioned conditions for their paper.

Internet Addresses

Internet Publishing Website : ftpj.otoiser.org

Internet Archive Digital Library : archive.org/details/@ftpj

Printing-on-Demand : pod@ftpj.otoiser.org

Principal Contact : principal-contact@ftpj.otoiser.org

Technical Support : technical-support@ftpj.otoiser.org

Editorial Team–Technical Support List : etts.ftpj.otoiser.org

Peer Discussion List : peers.ftpj.otoiser.org

Submissions : sub@ftpj.otoiser.org

Sample Paper Template : template.ftpj.otoiser.org

ARG NfP AoI

Antennas Research Group

Not-for-Profit Association of Individuals *

arg.op4.eu – arg@op4.eu

Hauptstraße 52, 2831 Scheiblingkirchen, Austria

- * The Constitution of Greece, Article: 12(3) 2008:
www.hellenicparliament.gr/en/Vouli-ton-Ellinon/To-Politevma
- * The Hellenic Supreme Court of Civil and Penal Law:
www.areiospagos.gr/en/ – Court Rulings:Civil|A1|511|2008

This document is licensed under a Creative Commons Attribution 4.0 International License – <https://creativecommons.org/licenses/by/4.0/>

Parameters Affecting the Lifetime of Transformer Oil in Distribution Transformers: Parameter Monitoring of 50 Transformers from the Athens Area

M.G. Danikas, E. Rapti, I. Liapis, A.B.B.Abd. Ghani *

Department of Electrical and Computer Engineering,
Democritus University of Thrace, Xanthi, Greece [1, 2]
Public Electricity Corporation, Athens, Greece [3]
High Voltage Cable Diagnostics, Distribution Unit TNB
Research Sdn. Bhd. Selangor, Malaysia [4]

Abstract

The aim of this paper is the study of various parameters affecting the ageing of transformer oil in distribution transformers of 20/0.4 kV. Fifty (50) samples of oil were taken from such transformers. The transformers function in the major Athens area, Greece. Parameters, such as breakdown strength, oil color, humidity, interfacial tension and $\tan\delta$ were taken into account. Transformer ageing and lifetime are strictly related to the rate of ageing of the whole insulating system, and mainly of the oil.

Absence of transpiring system with silica gel has as a result the increase of oil humidity. The lengthy use of transformers under heavy load, and consequently under high temperatures, is a main factor for oil ageing and oxidation. Especially in the last few years, the increased loads required by the transformers which have to do also with the climatic changes, have as a result the additional stressing of the oil. Various arcs, resulting from short circuits in the network, have as a consequence the production of gases and sludge. Such gases and sludge influence in a negative way the insulating properties of the oil as well as its rate of ageing. The role of silica gel is stressed.

Keywords

Transformer oil, distribution transformer, diagnostic methods, breakdown voltage, dielectric strength

Introduction

Transformer oil is a most important component in transformers [1]. Transformer oil ageing has been studied as well as the parameters and factors influencing its behavior under a variety of stresses (electrical, thermal, etc.) [2]-[5]. Faults in power and distribution transformers are rare (of the order of 1% - 2% per year), but when they occur, they have very serious technical and economic consequences. They may even lead to dangerous situations for human life and the environment. Main factors affecting the acceleration of ageing of the insulation of a transformer are humidity, high temperature, oxidation and the acidity of its oil. The role of chemical byproducts of the transformer insulation is also very important for its ageing. There is no single measurement able to give a whole picture of the state of a transformer. It must be noted that the variety of the diagnostic methods used, does not have as an aim the prediction of the useful remaining lifetime of the insulation, but it tries to reveal the increasing probability of faults and the corresponding decrease of the insulation reliability. Needless to say, that reduced reliability implies also reduced remaining

insulation lifetime.

With this in mind, in the context of the present paper, diagnostic methods were used in order to study the state of distribution transformers of the major Athens area. The transformers investigated were 20/0.4 kV. The whole work was carried with the aid of Public Power Company (PPC) of Greece, and more specifically with the aid of PPC Transformer Division. Oil was taken from 50 distribution transformers.

Diagnostic Methods

Warning signs about the state of a transformer are, among others, a big increase of partial discharges ($>> 2500$ pC), a visible deterioration because of foreign metallic and carbon particles, the presence of humidity in the solid insulation about 3-4 % and the presence of sludge.

Several diagnostic methods were used in order to see the quality of the transformers in question. The characterization of the oil color (DIN 51517 - ASTM D155) was performed through a device (chromometer) including standard glass disks and two glass jars with lid. The control of dielectric strength was measured by a typical Foster test cell, according to IEC 156/95 (Fig. 1).

The control of humidity in the oil was measured by a Metrohm - 684 KF Coulometer, which consisted of a glass container with a stirrer titration in which the reagent from container storage is added. The device is fully automated and once the experimenter gives the settings, it

measures the moisture content of the oil. The measurements were performed according to IEC 814. The control of interfacial tension (ASTM D971 - 91) was performed via a tensimeter, which gives the value in dynes per centimeter in a direct reading (Fig. 2).



Fig. 1: Device for the measurement of dielectric strength

The device that performed measurements of $\tan\delta$ and of resistivity, is the BAUR-DTL fully automated device for measuring dielectric losses of oils. Such a system has a fully automated process for measuring dielectric loss, relative dielectric constant and resistivity. The measurements were performed with a

system counting $\tan\delta$ values with maximum accuracy from 0.00001 to 4.0, measured according to IEC 247.

It is true that no single diagnostic method can give full information as to the state of a transformer. The aforementioned methods may give a better picture of its state.



Fig. 2: Tensimeter Cenco du Nouy

Experimental Results

The sampling was performed with due care, and according to general standard practice, i.e. during sampling there must not be any dust and humidity in the nearby space, the sampling cells must be clean and dry and they must be washed with oil from the transformer which is to be checked, the samples must be protected from light and they must be taken while the oil is hot but due time should pass before the various particles settle down. Sampling was done from the bottom of the transformers. The glass cells used for oil sampling were big enough so that they contained enough oil volume for additional measurements, if needed. No measurement was performed based on only one value or sample. All results must be verified with additional samples and measurements. Color measurements of the oil samples were based on specification DIN 51517 - ASTM D155 (Fig. 3). Dielectric strength measurements were based on specification IEC 156/95. Humidity measurements were based on specification IEC 814. Interfacial tension measurements were based on specification ASTM D971-91. Loss factor measurements were based on specification IEC 247.

Transformer oil is charac-

terized as good, if its color is not dark, its breakdown voltage more than 40 kV, its humidity less than 10 ppm, its resistivity more than $3 \text{ G}\Omega\cdot\text{m}$, its loss factor 0.1 , its interfacial tension more than 28 mN/m . It is acceptable if its breakdown voltage is between 30 to 40 kV, its humidity between 10 and 25 ppm, its resistivity between 0.2 and $3 \text{ G}\Omega\cdot\text{m}$, its loss factor between 0.1 and 0.5 , its interfacial tension between 22 and 28 mN/m . In the case of an acceptable oil, samplings should be carried out more frequently, and the content in foreign particles and contained water should be controlled. If the breakdown voltage and humidity are near the limit values, then the oil should be filtered and cleaned. An oil is poor when its color is dark (the dark color is an indication of pollution or ageing), its breakdown voltage less than 30 kV (in this case the oil should be replaced or thoroughly cleaned), its humidity more than 25 ppm (in such a case the oil should be replaced or thoroughly cleaned), its resistivity less than $0.2 \text{ G}\Omega\cdot\text{m}$, its loss factor more than 0.5 , its interfacial tension less than 22 mN/m (in this case a check should be carried out for the presence of sludge).

Generally it is suggested that in case one of the parameters mentioned (color, dielectric strength, humidity, interfacial tension, loss factor, resistivity) is acceptable, a more frequent sampling should be done in order to better monitor the oil quality. In the case any of the mentioned parameters is poor, cleaning or replacement of the oil is suggested. In any case, it is good to control all parameters concerned in order to have a clear picture of the state of the oil.

From the 50 oil samples investigated (taken from 50 distribution transformers), 3 of them showed breakdown voltage lower than 30 kV (i.e. percentage of 6%), 45 samples indicated humidity higher

than 25 ppm (i.e. percentage 90%), 28 samples presented interfacial tension lower than 15 dynes/cm (percentage 56%), whereas 44 samples showed a color higher than 1 1/2 (percentage 88%) (Fig. 4). It was evident from the data - mentioned in detail in [6] - that the more the number of years in service, the more the number of samples with lower dielectric strength. This is due to the fact that with the years there is also an increase of humidity in oil as well as an increase of the oxidation byproducts. Transformers which are in cities or in urban localities do not usually suffer lightning strokes, consequently the only stresses come from switching overvoltages and/or some high currents.



Fig. 3: Chromometer Hellige Comparator



Fig. 4: Typical glass colored disc

As the years pass by, humidity increases because fluctuations in temperature cause an increase of humidity entering the main oil volume. In distribution transformers having silica gel, the latter loses its absorbing property with an increasing number of years in service. Consequently silica gel should be replaced at regular intervals. The increasing number of years in service influences also the oil oxidation. Oxidation by-products in turn affect $\tan\delta$. The loss factor, however, is not influenced from the existence of humidity in the samples and for this reason is not a criterion for its exis-

tence. Interfacial tension is reduced with the years in service. This is due to the increasing quantity of humidity as well as to the byproducts of oxidation. There is, however, a number of samples with rather reduced interfacial tension although the number of years in service was not that big. This may be due to the quality of the oil used or to the fact that it contained only a small quantity of anti-oxidants. Finally, the oil color changes with the years in service. A change of color may also be due to the overcharging of a transformer.

Discussion

In this work, sampling from 50 transformers of 20/0.4 kV was carried out. Sampling and measurements were performed as suggested by the various international specifications [7]. All transformers were in the major Athens area. It should be noted that the transformers were not all from the same manufacturer. There were transformers from various manufacturers, both from Greece and abroad. This is one of the complications of the Greek Electricity System and certainly, this fact hinders any thought for a statistical approach. In case of poor oil color, this may be a symptom of humidity. Poor oil dielectric strength may imply that the oil should be cleaned or replaced. If the humidity level is high, the oil has to be again either cleaned or replaced. If the interfacial tension of oil is acceptable, this means that a control for the possible presence of by-products may be performed. Acceptable values of oil resistivity may be tolerated. In most cases, $\tan\delta$ was good. The parameters which changed most were the color, the oil dielectric strength, the levels of humidity and the oil interfacial tension. From the above, it is evident that one cannot pronounce any verdict

on the quality of a transformer oil based on only one parameter.

It is evident from the results that there was absence of a transpiring system with silica gel in most investigated transformers. This absence has as a result that the humidity of the atmosphere is in contact with the oil. The functioning of a transformer under heavy load, and consequently its functioning at high temperatures, results in an acceleration of its ageing. High temperatures cause oxidation of the oil. In addition to that, in the last years, increased loads – as a consequence of climatic changes (such as increased temperature and humidity) – are required and they result in the stressing of the oil. Arcs, because of short circuits, create gaseous byproducts and sludge. The latter influence in a negative way the dielectric strength of the oil. Another point which should be considered is that, with the continuing effort from the side of the manufacturers for the reduction in the size of the transformers, the oil tends to be more easily thermally stressed. This results in an accelerated rate of rise in temperature and an accelerated rate in its ageing.

Generally speaking, the frequent oil sampling helps in pointing out potential trouble spots in the network. It goes without saying that, as in this paper, a variety of measurements may give a better picture of the actual state of the transformers rather than isolated measurements or measurements confined only on a single quantity (e.g. dielectric strength). Ageing is a complex process and, as is well known, a variety of factors play a role. Ageing factors contribute not only to the ageing of the oil, but they may also interact among themselves, rendering thus the prediction of lifetime even more difficult [8], [9]. Breakdown of transformer oil is also a complex phenomenon determined mostly by the operating conditions [10].

As a way out of the various problems with transformer ageing, the construction of additional substations is proposed. This will reduce the load of each transformer. Needless to say that, the continuous checking of the whole distribution network and the requirement from the manufacturers to observe all the international norms and specifications, are necessary conditions for the good functioning of the whole system.

Special attention should be paid to the way one gets the oil samples. Sampling should be done with due care and care should be taken in order not for the sample to contain water. The samples should be taken from the transformers when the oil is still warm. Foreign particles should be allowed to settle at the bottom, so that no undue influence can be recorded in the various measurements.

In the case the results are contradictory, one has to repeat the sampling and the corresponding measurements. It is true that the manufacturers, try to reduce the production cost of the transformers and their respective materials by reducing the size of the transformers. This on one hand has as a result the possibly higher break-down strength of the oil, on the other hand, however, has as a result the faster increase of the oil temperature, and consequently the faster ageing and stressing of the mechanical parts of the transformer. Anyhow, a better maintenance of the distribution transformers should be followed as well as the placing of more transformers of larger power in localities with an increasing load demand.

The discussion as well as the conclusions of the pre-

sent paper are in line with previously published work [11], [12]. Such work was carried out on transformers of 20/0.4 kV as well as of 150/20 kV. A statistical approach cannot be offered for the time being, as it was done before [13], for the reasons given above.

It is to be hoped that the next steps in our work will be a classification of the distribution transformers according to manufacturer, according to their power (kVA) and according to the previous history (which includes years in service, all faults, short-circuits, lightning strokes, switching operations etc.). Thereafter, an effort will be made in order to statistically analyze the data.

Concluding, it is fitting to note that the present paper does not claim any originality regarding any new diagnostic techniques. This paper is an application of already existing and well known specifications. It is a continuation of an effort started few years ago, as mentioned in [7], [11], [12]. In this respect, the present paper presents new results, although the methods used are the same as in [6], [7], [11], [12]. In other words, this paper presents the state of transformer oil in some dis-

tribution transformers of a given area at a given moment in time. Needless to say that continuous monitoring is necessary in order to check and confirm the transformer oil quality. Continuous monitoring, however, is often not enough. If possible, it should go together with fault detection, namely partial discharge (PD) detection. PD detection can help preventing a defect from developing into a fault, e.g. a short circuit [14], [15], [16]. Nevertheless, condition monitoring as presented here, should be done on a regular basis.

Conclusion

Transformers of 20/0.4 kV from the major Athens area were investigated. Various parameters (oil color, dielectric strength, humidity, interfacial tension, $\tan\delta$ and resistivity) of the oil were studied with standard methods based on international specifications. No verdict on transformer oil quality can be based on only one parameter. A multitude of parameters is needed in order to pronounce a correct verdict on oil quality. The continuous control and monitoring of the distribution transformers is necessary in order to avoid problematic situations. The role of silica gel is emphasized.

Silica gel should be used in all transformers, so that humidity can be absorbed. The quantity of humidity increases with the number of years in service, consequently, distribution transformers should be checked at regular intervals.

References

- [1] Kind D., Kaerner H., "High-Voltage Insulation Technology", Eds. Friedr. Vieweg & Son, Braunschweig/Wiesbaden, Germany, 1985
- [2] Bell W.R., "Influence of specimen size on the dielectric strength of transformer oil", IEEE Transactions on Electrical Insulation, Vol. 12, 1977, pp. 281-292
- [3] Felici N.J., "Bubbles, partial discharges and liquid breakdown", Electrostatics 79, Institute of Physics Conference Ser. No. 48, 1979, pp. 181-190
- [4] Danikas M.G., "Breakdown of transformer oil", IEEE Electrical Insulation Magazine, Vol. 6, No. 5, 1990, pp. 27-34
- [5] Beroual A., Zahn M., Badent R., Kist K., Schwab A.J., Yamashita H., Yamazawa K., Danikas M., Chadband W.G., Torshin Y., "Propagation and structure of streamers in liquid dielectrics", IEEE Electrical Insulation Magazine, Vol. 14, 1998, pp. 6-17
- [6] Rapti E., "Parameters affecting the lifetime of transformer oil in distribution transformers", Diploma Thesis, Democritus University of Thrace, Department of Electrical and Computer Engineering, Power Systems Laboratory, Xanthi, Greece, 2009 (in Greek)
- [7] Liapis I., "Study of parameters influencing the ageing of the oil in distribution transformers", M.Sc. Thesis, Democritus University of Thrace, Department of Electrical and Computer Engineering, Power Systems Laboratory, Xanthi, Greece, 2010 (in Greek)
- [8] Kelen A., "Trends in PD diagnostics", IEEE Transactions on Dielectrics and Electrical Insulation, Vol. 2, 1995, pp. 529-534
- [9] Bernstein B.S., Brancato E., "Aging of equipment in the electric utilities", IEEE Transactions on Electrical Insulation, Vol. 28, 1993, pp. 866-875

- [10] Naidu M.S., Kamaraju V., "High Voltage Engineering", Eds. Tata McGraw-Hill Publishing Co. Ltd., New Delhi, India, 1995
- [11] Danikas M.G., Liapis I., "A study of parameters affecting the ageing of transformer oil in distribution transformers", Proceedings of 17th International Conference on Dielectric Liquids (ICDL 2011), Trondheim, Norway, 26-30 June 2011, Session 02, Paper 1
- [12] Danikas M.G., Missas S., Liapis I., "Factors affecting the ageing of transformer oil in 150/20 kV Transformers", Proceedings of 17th International Conference on Dielectric Liquids (ICDL 2011), Trondheim, Norway, 26-30 June 2011, Session 06, Paper 1
- [13] Spartalis S.I., Danikas M.G., Andreou G.P., Vekris G., "Statistical study of the oil dielectric strength in power distribution transformers", Journal of Electrical Engineering, Vol. 59, 2008, pp. 68-74
- [14] Borsi H., "Probleme der Teilentladungs-(TE-)Ueberwachung am Beispiel von TE-Messungen an Leistungstransformatoren im Betrieb", book (editors: Koenig D., Narayana Rao Y., "Teilentladungen in Betriebsmitteln der Energietechnik", vde verlag gmbh, Berlin und Offenbach, Germany, 1993), pp. 275-292
- [15] Gulski E., Smit J.J., Brooks R., Turner M., "Experiences with digital analysis of discharges in high voltage components", IEEE Electrical Insulation Magazine, Vol. 15, No. 3, 1999, pp. 15-24
- [16] Marques A.P., De Jesus Ribeiro C., Bezerra Azevedo C. H., Dos Santos J.A.L., De carvalho Sousa F.R., da Cunha Brito L., "Power transformer disruptions - A case study", IEEE Electrical Insulation Magazine, Vol. 30, No. 2, 2014, pp. 17-21

Previous Publication in FUNKTECHNIKPLUS # JOURNAL

"Interfaces in High Voltage Engineering: A Most Important Question for Conventional Solid Insulating Materials as well as for Nanocomposite Polymers", Issue 4, pp. 7-31

*** About The Authors**

Michael Danikas, Issue 2, p. 39

Elli Rapti, is a graduate of Democritus University of Thrace, Department of Electrical and Computer Engineering, Xanthi, Greece. She is currently employed in a private-owned company. Her research interests are in transformer oil diagnostics.

Ioannis Liapis, is a graduate of Democritus University of Thrace, Department of Electrical and Computer Engineering, Xanthi, Greece, and is currently working with Public Power Corporation in Athens. His research interests are in transformer oil diagnostic techniques.

j-liapis@hotmail.com

Ahmad Basri Bin Abdul Ghani, Dr., is a researcher at TNB Research Institute in Selangor, Malaysia. His research interests include among other topics, power cable diagnostics, transformer oil diagnostics and partial discharge measurements.

abasri.aghani@tnbr.com.my

[This Page Intentionally Left Blank]

[This Page Intentionally Left Blank]

[This Page Intentionally Left Blank]

[This Page Intentionally Left Blank]

In case of any doubt,
download the genuine papers from
genuine.ftpj.otoiser.org

FRONT COVER VIGNETTE

A faded synthesis of an anthemion rooted in a meandros

The thirteen-leaf is a symbol for a life tree leaf.
"Herakles and Kerberos", ca. 530–500 BC,
by Paseas, the Kerberos Painter,
Museum of Fine Arts, Boston.

www.mfa.org/collections/object/plate-153852

The simple meandros is a symbol for eternal immortality.
"Warrior with a phiale", ca. 480–460 BC,
by Berliner Maler,
Museo Archeologico Regionale "Antonio Salinas" di Palermo.

commons.wikimedia.org/wiki/File:Warrior_MAR_Palermo_NI2134.jpg